



Granite[®] Standard

Inspired by Nature



Properties

- Good corrosion resistance
- Good formability
- Thermosetting paint
- Surface treatment and paint: free of hexavalent chromium and heavy metals

Applications

Basic coating for outdoor applications (cladding, roofing and accessories, air conditioners)

Description

Thickness ⁽¹⁾	25 microns
Composition	Front: 5 microns primer + 20 microns top coat Back: 5, 7, 10 or 12 microns backing coat Double-side finish available
Gloss (Gardner 60°) ⁽¹⁾	30 GU Other gloss levels on request
Colours	Colour palette Other colours on request
Appearance	Smooth
Temporary protection (optional)	Self-adhesive film or heat-sealed film

Performance

Adhesion of the coating (T-bend)	≤ 2 T
Resistance to cracking on bending (T-bend)	≤ 3 T
Impact resistance	18 J
Surface "pencil" hardness	HB to H
Clemen scratch resistance	≥ 2 kg
Corrosion resistance: • Salt spray test • Corrosion resistance category	360 hours RC3
Condensation resistance (QCT)	1000 hours
UV resistance: • QUV (UVA + H ₂ O) test (2000 hours) • UV resistance category	ΔE ≤ 5; GR ≥ 30% RUV2
Fire behaviour classification (EN 13501-1)	A1
Resistance to acids and bases	Good
Resistance to solvents: • Aliphatics and alcohols • Ketones • Aromatics	Very good Low Good to very good
Resistance to mineral oils	Very good

Automatic guarantee

• Non-perforation of the sheet metal	≤ 10 years, depending on the external environment
• Non-delamination of the paint	≤ 10 years, depending on the external environment
• Aesthetic appearance (ΔE ≤ 5; Gloss retention ≥ 30%)	≤ 5 years, depending on the geographic location and the paint colour category

Remarks

These performance characteristics refer specifically to metallic coating Z225, ZA200 and Optigal[®] ZM100 (guaranteed minimum).
If any product (film, oil, foam, glue, paint etc) is to be applied after coil delivery, compatibility with the coating needs to be checked first.
Although we take great care to reproduce the same aesthetic aspect on each coil, ArcelorMittal cannot guarantee the visual consistency from one batch to another. Consequently, you need to consider placing one single order for one building; standard samples can only serve as a guide.

(1) Nominal value, tolerance according to EN 10169